

VI semiconductors, group IV semiconductors and compounds, metal oxides, metal fluorides, diamond, yttrium aluminum garnet, and combinations thereof.

10. (Previously Amended) The light emitting device of Claim 1, wherein said optical element is formed from a material selected from the group of zirconium oxide, sapphire, GaP, ZnS, materials containing lead oxide, and SiC.

11. (Original) The light emitting device of Claim 1, wherein said optical element includes one or more luminescent materials that convert light of a wavelength emitted by said active region to at least another wavelength.

12. (Original) The light emitting device of Claim 1, wherein said optical element is coated with one or more luminescent materials that convert light of a wavelength emitted by said active region to at least another wavelength.

13. (Canceled).

14. (Previously Amended) The light emitting device of Claim 1, wherein said ratio is greater than about two.

15. (Original) The light emitting device of Claim 1, wherein said stack is located in a recess of a surface of said optical element.

16. (Original) The light emitting device of Claim 1, wherein a refractive index of said optical element for light emitted by said active region is greater than about 1.5.

17. (Original) The light emitting device of Claim 16, wherein said refractive index is greater than about 1.8.

18. (Original) The light emitting device of Claim 1, wherein a refractive index of said optical element is greater than or equal to a refractive index of said semiconductor layers for light emitted by said active region.

19. (Original) The light emitting device of Claim 1, further comprising contacts electrically coupled to said semiconductor layers to apply a voltage across said active region.

PATENT LAW
GROUP LLP
2035 N. FIRST ST.
SUITE 223
SAN JOSE, CA 95134
(408) 382-0480
FAX (408) 382-0481

20. (Original) The light emitting device of Claim 19, wherein at least one of said contacts is highly reflective for light emitted by said active region and is located to reflect said light toward said optical element.

21. (Original) The light emitting device of Claim 1, further comprising at least one beveled side located to reflect light emitted from said active region toward said optical element.

22. (Original) The light emitting device of Claim 1, further comprising at least one layer highly reflective for light emitted by said active region located to reflect said light toward said optical element.

23. (Original) The light emitting device of Claim 1, wherein said transparent optical element is directly bonded to at least one of said semiconductor layers.

24. (Original) The light emitting device of Claim 1, wherein said stack comprises a transparent superstrate layer disposed above said semiconductor layers and directly bonded to said optical element.

25. (Original) The light emitting device of Claim 24, wherein superstrate layer has a refractive index for light emitted by said active region greater than about 1.8.

26. (Original) The light emitting device of Claim 24, wherein said superstrate layer is formed from a material selected from the group of sapphire, SiC, GaN, and GaP.

27. (Previously Amended) The light emitting device of Claim 24, wherein said optical element comprises one of ZnS, zirconium oxide, SiC, materials containing lead oxide, and sapphire, said superstrate comprises one of SiC, GaN, and sapphire, and said semiconductor layers comprise a III-Nitride semiconductor.

28. (Original) The light emitting device of Claim 27, further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region; said first contact and said second contact disposed on a same side of said stack.

PATENT LAW
GROUP LLP
2635 N. FIRST ST.
SUITE 220
SAN JOSE, CA 95134
(408) 382-0480
FAX (408) 382-0481

29. (Previously Amended) The light emitting device of Claim 24, wherein said optical element is formed from one of zirconium oxide, sapphire, material containing lead oxide, SiC, ZnS, and GaP, said superstrate is formed from a III-Phosphide material, and said semiconductor layers comprise one of III-Phosphide semiconductors and III-Arsenide semiconductors.

30. (Previously Amended) The light emitting device of Claim 27, further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region; said first contact and said second contact disposed on a same side of said stack.

31. (Original) The light emitting device of Claim 1, further comprising a transparent bonding layer disposed between said optical element and a surface of said stack, said transparent bonding layer bonding said optical element to said stack.

32. (Previously Amended) A light emitting device having a stack of layers including semiconductor layers comprising an active region, said device comprising:

a transparent optical element bonded to said stack by a bond at an interface disposed between said optical element and said stack; and

a transparent bonding layer comprising a material different from a material forming the optical element, the transparent bonding layer being disposed between said optical element and a surface of said stack and bonding said optical element to said stack.

33. (Original) The light emitting device of Claim 31, wherein said transparent bonding layer includes one or more luminescent materials that convert light of a wavelength emitted by said active region to at least another wavelength.

34. (Original) The light emitting device of Claim 31, wherein said bonding layer has an index of refraction greater than about 1.5 for light emitted by said active region.

PATENT LAW
GROUP LLP
2035 N. FIRST ST.
SUITE 223
SAN JOSE, CA 95134
(408) 382-0480
FAX (408) 382-0482

35. (Original) The light emitting device of Claim 34, wherein said index of refraction is greater than about 1.8.

36. (Original) The light emitting device of Claim 31, wherein said bonding layer has a thickness less than about 500 Angstroms.

37. (Original) The light emitting device of Claim 31, wherein said surface includes a surface of one of said semiconductor layers.

38. (Original) The light emitting device of Claim 31, wherein said surface includes a surface of a transparent superstrate layer disposed above said semiconductor layers.

39. (Original) The light emitting device of Claim 38, wherein said superstrate layer has a refractive index for light emitted by said active region greater than about 1.8.

40. (Original) The light emitting device of Claim 38, wherein said superstrate layer is formed from a material selected from the group of sapphire, SiC, GaN, and GaP.

41. (Previously Amended) The light emitting device of Claim 38, wherein said optical element comprises one of ZnS, zirconium oxide, materials containing lead oxide, SiC, and sapphire, said superstrate comprises one of SiC, GaN, and sapphire, and said semiconductor layers comprise a III-Nitride semiconductor.

42. (Original) The light emitting device of Claim 41, further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region; said first contact and said second contact disposed on a same side of said stack.

43. (Previously Amended) The light emitting device of Claim 38, wherein said optical element is formed from one of zirconium oxide, sapphire, materials containing lead oxide, SiC, ZnS, and GaP, said superstrate is formed from a III-Phosphide material, and said semiconductor layers comprise one of III-Phosphide semiconductors and III-Arsenide semiconductors.

PATENT LAW
GROUP LLP
2635 N. FIRST ST.
SUITE 223
SAN JOSE, CA 95134
(408) 382-0480
FAX (408) 382-0481

44. (Original) The light emitting device of Claim 43, further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region; said first contact and said second contact disposed on a same side of said stack.

45-62. (Canceled).

63. (Previously Added) The light emitting device of Claim 31, wherein said transparent bonding layer includes a lead oxide.

64. (Previously Added) The light emitting device of Claim 31, wherein said transparent bonding layer includes a tungsten oxide.

65. (Previously Added) The light emitting device of Claim 32, wherein said transparent bonding layer includes one or more luminescent materials that convert light of a wavelength emitted by said active region to at least another wavelength.

66. (Previously Added) The light emitting device of Claim 32, wherein said bonding layer has an index of refraction greater than about 1.5 for light emitted by said active region.

67. (Previously Added) The light emitting device of Claim 66, wherein said index of refraction is greater than about 1.8.

68. (Previously Added) The light emitting device of Claim 32, wherein said bonding layer has a thickness less than about 500 Angstroms.

69. (Previously Added) The light emitting device of Claim 32, wherein said surface includes a surface of one of said semiconductor layers.

70. (Previously Added) The light emitting device of Claim 32, wherein said surface includes a surface of a transparent superstrate layer disposed above said semiconductor layers.

PATENT LAW
GROUP LLP
2035 N. FIRST ST.
SUITE 220
SAN JOSE, CA 95131
(408) 382-0480
FAX (408) 382-0481

71. (Previously Added) The light emitting device of Claim 70, wherein said superstrate layer has a refractive index for light emitted by said active region greater than about 1.8.

72. (Previously Added) The light emitting device of Claim 70, wherein said superstrate layer is formed from a material selected from the group of sapphire, SiC, GaN, and GaP.

73. (Previously Added) The light emitting device of Claim 70, wherein said optical element comprises one of ZnS, zirconium oxide, materials containing lead oxide, SiC, and sapphire, said superstrate comprises one of SiC, GaN, and sapphire, and said semiconductor layers comprise a III-Nitride semiconductor.

74. (Previously Added) The light emitting device of Claim 73, further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region; said first contact and said second contact disposed on a same side of said stack.

75. (Previously Added) The light emitting device of Claim 70, wherein said optical element is formed from one of zirconium oxide, sapphire, materials containing lead oxide, SiC, ZnS, and GaP, said superstrate is formed from a III-Phosphide material, and said semiconductor layers comprise one of III-Phosphide semiconductors and III-Arsenide semiconductors.

76. (Previously Added) The light emitting device of Claim 75, further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region; said first contact and said second contact disposed on a same side of said stack.

77. (Previously Added) The light emitting device of claim 32 wherein said transparent bonding layer is formed from a material selected from the group of optical glass,

PATENT LAW
GROUP LLP
2034 N. FIRST ST.
SUITE 223
SAN JOSE, CA 95134
(408) 382-0481
FAX (408) 382-0481

chalcogenide glass, III-V semiconductors, II-VI semiconductors, group IV semiconductors, metals, metal oxides, metal fluorides, yttrium aluminum garnet, phosphides, arsenides, antimonides, nitrides, and combinations thereof.

78. (Previously Added) The light emitting device of claim 32 wherein said transparent bonding layer comprises an oxide of lead.

79. (Previously Added) The light emitting device of claim 32 wherein said transparent bonding layer comprises an oxide of tungsten.

80. (Currently Amended) A light emitting device having a stack of layers including semiconductor layers comprising an active region, said device comprising:

an optical element bonded to said stack, the optical element comprising one of ~~materials containing lead oxide~~ sapphire and SiC; and

a first contact and a second contact electrically coupled to apply a voltage across said active region;

wherein said stack of layers comprises at least one III-Phosphide semiconductor layer and said first contact and said second contact are disposed on a same side of said stack.

81. (Canceled).

82. (Currently Amended) A light emitting device having a stack of layers including semiconductor layers comprising an active region, said device comprising:

an optical element bonded to said stack; and

wherein said optical element comprises one of ~~a material containing lead oxide, a material containing tungsten oxide~~ sapphire and SiC.

83. (Previously Added) The device of Claim 82 further comprising a first contact and a second contact electrically coupled to apply a voltage across said active region;

wherein said stack of layers comprises at least one III-Nitride semiconductor layer and said first contact and said second contact are disposed on a same side of said stack.

84. (Previously Added) The device of Claim 82 wherein the stack comprises a transparent superstrate, and optical element is bonded to a surface of the transparent substrate.

PATENT LAW
GROUP LLP
2535 N. FIRST ST.
SUITE 223
SAN JOSE, CA 95134
(408) 382-0481
FAX (408) 382-0481